Goldbronze-Anlegelack
Gold Bronce Powder

Kurzinformation:
Basis Lackschicht mit Anlegelack # 263060
Das farbige Pulver (26309 .. Metallpigment) wird in den Lack eingemischt.
Versiegelung mit Überzugslack # 263065
Durch diesen wird ein Tiefenglanz erreicht und gleichzeitig ein Schützt vor Oxidation.
Das Pigment oxidiert (verdunkelt), wenn es nicht versiegelt wird.

Art.Nr	Art.Bez.1	Mischungsverhältnis:	Verdünnung
263030	Spritzspachtel, für Gußplatten, gelbgold	Je nach Spritzpistole und Druck (von 0-5%). **Normal muss nicht verdünnt werden.**	263070
263060	Goldbronze-Anlegelack, Mischlack für Farbpulver	Je nach Spritzpistole und Druck (von 0-5%). **Normal muss nicht verdünnt werden.**	263070
263065	Überzugslack für Goldbronze-Anlegelack	Je nach Spritzpistole und Druck (von 0-5%). **Normal muss nicht verdünnt werden.**	263070
26309..	Farb-Pulver, für Anlegelack	Maximal 10 % Gewicht Pulver zum Gewicht des Lackes. Bei Neuauftrag.Für Ausbesserarbeiten wenn weniger Deckkraft erforderlich genügt max 5% Farbpulver.	
263070	Verdünnung für Goldbronze-Anlegelack		

Goldbronze-Anlegelack
Gold Bronce Powder

Short Information:
Processing instructions after priming:
Base coat of varnish with application varnish # 263060
The colored powder (26309 .. metal pigment) is mixed into the paint.
Sealing with top coat # 263065
This creates a deep gloss and at the same time protects against oxidation.
The pigment will oxidize (darken) if not sealed.

Art.No	Name 1	Mix ratio:	Dilution
263030	Spray filler, for frames, gold	Depends on airbrush and pressure (from 0-5%). **Usually dilution is not necessary**	263070
263060	Mixing lacquer for gold bronce colour powder.	Depends on airbrush and pressure (from 0-5%). **Usually dilution is not necessary.**	263070
263065	Top coat for mixing lacquer.	Depends on airbrush and pressure (from 0-5%). **Usually dilution is not necessary**	263070
26309..	Colour powder for mixing lacquer.	Max. 10 % weight of powder to weight of lacquer for repainting. For repair work when less covering power is required, max 5% colour powder is sufficient.	
263070	Dilution for mixing lacquer for gold bronce powder.		